

3M Thermal Transfer Polyimide Label Material 7812

Technical Data

July, 2011

Product Description

3M™ Thermal Transfer Polyimide Label Material 7812 is a polyimide film product that offers ultra-high temperature performance. This label product utilizes 3M™ Adhesive 100, that can withstand up to 450°F (232°C) short-term heat resistance, has excellent solvent resistance, and exhibits low outgassing characteristics.

Construction

(Calipers are nominal values.)

Facestock	Adhesive	Liner
2.0 mils (51 microns) Polyimide Film 1.0 mil (25 microns) Matte White Thermal Transfer Printable Topcoat	2.0 mil (51 microns) 100 Acrylic	3.2 mils (76 microns) 50# Densified Kraft

Features

- Matte white thermal transfer topcoat for easy readability of barcodes and variable information.
- Adhesive will not degrade when exposed to a wide variety of harsh processing conditions. This adhesive also offers exceptional shear strength even at elevated temperatures.
- 50# densified kraft liner assures consistent die cutting.
- UL Recognized and CSA Accepted. See UL (File MH16411) and CSA (File 99316) listings for details.

Application Ideas

- Printed circuit board tracking labels that see the following conditions:
 - Solder reflow;
 - Top and/or bottom side wave solder;
 - Most cleaning processes and chemicals.
- Labeling on parts exposed to high temperatures.

3M™ Thermal Transfer Polyimide Label Material 7812

Typical Peel Adhesion Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Adhesion: 180° peel test procedure is ASTM D 3330.

	Initial (10 Minute Dwell/RT)		Conditioned for 3 Days at Room Temperature 72°F (22°C)	
	180° Peel		180° Peel	
Surface	Oz./In.	N/100 mm	Oz./In.	N/100 mm
Stainless Steel	32	35	53	58
Polycarbonate	34	37	58	63
Epoxy PC Board	44	48	62	68

	Conditioned for 3 Days at 120°F (49°C)		Conditioned for 24 Hours at 90°F (32°C) at 90% relative humidity	
	180° Peel		180° Peel	
Surface	Oz./In.	N/100 mm	Oz./In.	N/100 mm
Stainless Steel	66	72	64	70
Polycarbonate	56	61	62	68
Epoxy PC Board	67	73	44	48

3M™ Thermal Transfer Polyimide Label Material

7812

Environmental Performance

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

The properties defined are based on four hour immersions at room temperature (72°F/22°C) unless otherwise noted. Samples were applied to stainless steel panels 24 hours prior to immersion and were evaluated one hour after removal from the solution for peel adhesion. Adhesion measured at 180° peel angle (ASTM D 3330) at 12 inches/minute.

Chemical Resistance:

Chemical	Adhesion to Stainless Steel		Appearance	Edge Penetration
	Oz./in.	N/100 mm	Visual	Millimeters
Isopropyl Alcohol	47	51	No change	0
Detergent 1% Alconox® Cleaner	53	58	No change	0
Engine Oil (10W30) @ 250°F (121°C)	96	105	No change	0
Water for 48 hours	54	59	No change	0
pH 4	53	58	No change	0
pH 10	50	55	No change	0
409® Formula	51	56	No change	0
Toluene	25	27	No change	0
Acetone	13	14	No change	0
Brake Fluid	53	58	No change	2
Gasoline	39	43	No change	1
Diesel Fuel	49	54	No change	0
Mineral Spirits	47	51	No change	0
Hydraulic Fluid	49	54	No change	0

Temperature Resistance:

530°F (277°C) for 30 seconds:

no significant visual change

500°F (260°C) for 7 minutes:

slight browning

-40°F (-40°C) for 24 hours:

no significant visual change

Humidity Resistance:

24 hours at 100°F (38°C) and 100% relative humidity:

no significant change in appearance or adhesion

Accelerated Aging:

ASTM D 3611:

96 hours at 150°F (65°C) and 80% relative humidity

Application Techniques

For maximum bond strength, the surface should be clean and dry. Typical cleaning solvents are heptane and isopropyl alcohol.*

For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, below 50°F (10°C), can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds can be achieved through increased rubdown pressure.

*When using solvents, read and follow the manufacturer's precautions and directions for use.

3M™ Thermal Transfer Polyimide Label Material 7812

Printing

Facestock is topcoated and is designed for thermal transfer printing.

- Recommended Ribbons
Ricoh; D110A
Union Chemicar; US300

The following ribbons can be used but may require higher burn temperatures:

- Sony; 5070
- Mid City Columbia; CGL-80HE
- Dai Nippon; R510

Printed Label Performance:

Samples were printed with a Ricoh D110A resin ribbon on Zebra 170xi printer at a rate of 2 in./min. and a burn setting of 22. Labels were printed with a 3:1 ratio barcode with 6 mil X-dimension. Printed labels were exposed to the listed conditions, which are representative of PCB assembly conditions. After chemical exposure, labels were rinsed with tap water, dried and examined.

Condition	Printed Contrast Signal (PCS)	Read Rate
3M™ Label Material 7812 Control	97	100
530°F, 30 sec.	97	100
500°F, 7 min.	94	100
IPA 75%, 106°F, 15 min.	97	100
IPA 100%, RT 2 min.	97	100
Deionized Water, 140°F, 5 min.	97	100
Alconox® 10%, 135°F, 2 min.	97	100
D-Limonene RT, 2 min.	97	100
Monoethanolamine, 135°F, 2 min.	97	100
BIOACT® EC-7R, 77°F, 10 min.	92	100
BIOACT® EC-15, 77°F, 10 min.	92	100
Wave Solder	95	100

The Print Contrast Signal, PCS, was determined using a PSC QUICKCHECK™ 850, with a 0.003" aperture, 660 nm wavelength. The read rate was determined using a PSC laser diode scanner, model 4100. Wave soldering was performed on an Electrovert Co., Microline 250 wave solder machine. Preheat temperature was 250°F (121°C), solder temperature was 470°F (243°C), line speed was 2 ft./min. Boards were pre-sprayed with a Kester Solder Co. 923 flux.

Convertability

The exceptional shear strength of 3M™ Acrylic Adhesive 100 is an excellent choice for high temperature applications such as printed circuit boards. Specifically designed to be compatible with thermal transfer technologies. Adhesive processing issues are not anticipated when proper roll tensions, handling and storage conditions are used. Please refer to the die cutting section of this data page or the "Guide to Converting and Handling Label Products" technical bulletin for additional information.

3MTM Thermal Transfer Polyimide Label Material 7812

Die-Cutting	Rotary die-cutting is recommended.
Packaging	Finished labels should be stored in plastic bags.
Storage	Store at room temperature conditions of 72°F (22°C) and 50% relative humidity.
Shelf Life	If stored under proper conditions, product retains its performance and properties for two years from date of manufacture.
Technical Information	The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.
Product Use	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.
Warranty, Limited Remedy, and Disclaimer	Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.
Limitation of Liability	Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2008

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2008 standards.

3

Industrial Adhesives and Tapes Division Converter Markets

1030 Lake Road
Medina, OH 44256-0428
800-422-8116 • 877-722-5072 (fax)
www.3M.com/converter



*Recycled Paper
40% pre-consumer
10% post-consumer*

3M is a trademark of 3M Company.
BIOACT is a registered trademark of MicroCare.
PSC QUICKCHECK is a trademark of PSC.
Alconox is a registered trademark of Alconox, Inc.
409 is a registered trademark of Clorox.
Printed in U.S.A.
©3M 2011 70070948107 (7/11)